



Owensboro Specialty Polymers, Inc.
Chemistry that Connects, People that Care

OSP Serfene PVdC Latex Physical Property Comparison Chart

Product	TS %	pH	Viscosity in cps (Brookfield RVT #1 @ 20 rpm)	Latex Density in lbs./gallon	Surface Tension in dynes/cm	MFFT °F	MFFT °C	Alcohol Tolerant (IPA)	Stability on Freezing	Shelf Life in days	Tg of film °F	Tg of film °C
195	58	3	10	10.9	30	NA	NA	Yes-10% max.	None	360	63.7	17.6
400	58	1.8	10	10.9	38	NA	NA	No	None	180	64.2	17.9
546L	46	2.3	35	10.3	51	NA	NA	Yes-15% max.	None	180	48.2	9.0
777	55	4	15	9.8	34	59	15	Yes	None	180	71.6	22.0
2010	50	1.8	10	10.45	46	NA	NA	Yes-10% max.	None	70	72.7	22.6
2026	45	1.5	12*	10.45	38	NA	NA	NA	None	180	NA	NA
2060	50	1.5	10	10.45	45	NA	NA	Yes	None	180	72.9	22.7
2061	50	1.5	10	10.45	38	NA	NA	Yes	None	180	72.9	22.7

* Brookfield LVF #1 @ 50 rpm.

NA = Not available at this time.

These are all anionic polymers.

These are representative properties, not product specifications.

Shelf life is not guaranteed and is highly influenced by storage conditions.

OSP_PPC_Serfene_Rev.3.0

Revision Date: December 2, 2015