

TECHNICAL DATA SHEET

Shuman Compound:

Polycarbonate 910 Utility Black, 920 Black, 980Grey, 930 White, 900 Clear

Offers this combination of properties:

Good impact strength, Easy processability, Good surface gloss, Good heat resistance, Excellent weatherability, Excellent color stability, Self-extinguishing

TYPICAL PROPERTIES

MECHANICAL PROPERTIES Izod Impact Strength (Notched, 1/8" Thick Specimen) Rockwell Hardness Tensile Strength	<u>VALUE</u> 12 70 9500	<u>UNITS</u> FT-LBS/IN M PSI	TEST METHODS ASTM D-256 ASTM D-785 ASTM D-638
THERMAL PROPERTIES Heat Deflection Temperature @ 264 PSI Vicat Softening Temperature	262 310	deg. F deg. F	ASTM D-648 ASTM D-1525
OTHER PROPERTIES Specific Gravity Melt Flow Rate	1.2 10 (+/-2) 15 (+/-2) 20 (+/-2)	GM/10 MIN.	ASTM D-792 ASTM D-1238

SUGGESTED PROCESSING CONDITIONS

DRYING CONDITIONS:		<u>TEMPERAT</u> <u>MIN.</u>	<u>URE (deg. F)</u> <u>MAX.</u>	<u>TIME (F</u> MIN.	<u>IOURS)</u> MAX.	
Dehumidifyir	ng Dryer	250	260	2-3	24	
Tray Dryer	NOTE: Depth of granules in tray dryer should not exceed 1 in. (25.4 mm)	250	260	4-6	24	

TEMPERATURE CONDITIONS:

510-550F

NOTICE: THE INFORMATION CONTAINED HEREIN IS BASED ON WHAT WE BELIEVE TO BE RELIABLE DATA, BUT SHUMAN PLASTICS, INC. MAKES NO WARRANTIES EXPRESS OR IMPLIED, INCLUDING, BUT NOT LIMITED TO, THE IMPLIED WARRANTIES OR MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE. BECAUSE SHUMAN HAS NO CONTROL OVER THE USE TO WHICH OTHERS MAY PUT THE PRODUCT, IT DOES NOT SUGGEST OR REPRESENT THAT THE SAME RESULTS AS THOSE REFERRED TO HEREIN WILL BE OBTAINED BY ANOTHER USER. EACH USER OF THE PRODUCT AND THE COMPOSITIONS MENTIONED HEREIN SHOULD MAKE HIS OWN TESTS PRIOR TO PURCHASE TO DETERMINE THE PRODUCT'S SUITABILITY FOR HIS OWN PARTICULAR USES.

NOTHING CONTAINED HEREIN IS TO BE CONSTRUED AS A RECOMMENDATION FOR THE USE IN VIOLATION OF ANY EXISTING PATENT, FOREIGN OR DOMESTIC, OR OF APPLICABLE LAWS AND REGULATIONS.

DATA SHOWN ARE THE AVERAGE RESULTS OF OUR OWN TESTS AND SHOULD NOT BE USED FOR SPECIFICATIONS