



REGAL RUBBER PARTNERSHIP LLP

CARTMORE INDUSTRIAL ESTATE, LOCHGELLY, FIFE, KY5 8LL Tel: 01592 780632 Fax: 01592 782888
 Email: rollers@regalrubber.co.uk www.regalrubber.co.uk

Material Data Sheet

Material Reference	1642
Colour	BLACK
To Specification	COMMERCIAL

Basic Properties	Value	Test Method	Unit
Base Polymer Type	SBR/CR		
Indentation Hardness	60 Shore A -4 +5	ASTM D2240 00	Degrees
Specific Gravity	1.5 +/- 0.05	ASTM D792	g/cm ³
Tensile Strength - Minimum	3	ASTM D412	Mpa
Elongation @ Break - Minimum	250	ASTM D412	%
Minimum Continuous Working Temperature	-20		°C
Maximum Continuous Working Temperature	70		°C
Maximum Intermittent Working Temperature	90		°C
Compression Set 70 Degrees 22 Hours	35% Max	ASTM D395 Method B	%
Insertion Type	Special Order for Insertion		

Guidelines for Use (It is the Customers responsibility to ensure suitability of Use)

Food Use Suitability	<i>Not Recommended</i>
Abrasion Resistance	<i>Moderate</i>
Ozone Weather Resistance	<i>Moderate</i>
Flame Retardency	<i>Moderate</i>
Electrical Resistance	<i>Not Recommended</i>
General Purpose	<i>Good</i>

Additional Information

None

Important Information about the Data provided on this Data Sheet

This datasheet has been carefully compiled to advise you, our customer, in the best possible way. The information, figures, test values, and data correspond to actual engineering standards and are the result of many years of tests and trials. As individual operating conditions influence the application of each product, the information supplied in this datasheet can only be seen as a rough guideline. In every case it is the sole responsibility of the customer to evaluate his individual requirements, in particular whether the specified properties of our products are sufficient for the intended use. This datasheet is subject to alteration without prior notice. All mentioned values contained herein are guiding values representing long-term experience averages. Please be aware that Test Results for individual Material Batches will only be provided if requested at the time of order and may be subject to additional charges and/or lead times. This Data Sheet supercedes all previous data sheets and any other data previously provided either Verbally, Electronic or Written, with reference to the above Material Grade.