

DAMAR QL FAST DRY

Description

The next generation of high quality, high performance, waterborne road marking paint with exceptional fast drying characteristics.

Applied by spray.

Available: 20 litre, 200 litre, 1000 litre

Typical Uses

- As a long lasting road marking paint.
- For use on bituminous and concrete substrates.
- Where excellent glass bead holding is required.

Properties

Resin System	Acrylic Emulsion
Pigmentation	Titanium Dioxide, Hard wearing extenders
Finish	Matt
Colour	White. Other colours available on request
Dilution Rate	Use as supplied
Volume Solids	65% ± 2.0%
Theoretical Coverage	3.0 – 3.7 m ² /litre @ 220 - 180 µm DFT
Dry Time @ 25°C	Touch 2½ minutes, Recoat 20 minutes
Number of Coats	1
Clean Up	Water. For a thorough clean of equipment Damar Thinners PF 5 is recommended.

Performance / Limitations

- Approved for New Zealand Transport Agency M7 specification road marking use.
- Fast drying (M7 2017 specification classification rapid dry).
- Excellent resistance to bleeding.
- Excellent adhesion to aged road marking paint.
- Improved retention of glass beads (when compared to alkyd based paints).

- Dry times will be longer in cold or high humid, windless weather.
- NOT recommended for use over damp or wet surfaces.
- NOT recommended for use under 10°C. Below this temperature product will not form a film and adhere to substrate.

- Application to concrete is problematic due to large variations in drying agents and surface finishes available, plus surface contaminations.
- For application to concrete surfaces please refer to concrete application sheet

Preparation

- Surfaces must be clean, dry, free from oil, grease, lichen, etc. and any loose, flaky material.
- Can be applied to bare, unprimed or unsealed bitumen based surfaces*

*For concrete painting see concrete preparation information sheet

Application

- Stir thoroughly before use.
- Recommended application method is by spraying, either airless or conventional.
- May be thinned up to 5% by volume with water to aid application.
- For first coat application to new or aged hot mix on car parks or tennis courts etc, apply a dust coat of approximately 50 Microns DFT, leave to dry for 24 hours minimum then apply second coat to desired film build.

Approvals

New Zealand NZTA M/7 2017 CEO* AL0*
 Australia APAS 0041/5

*M7 approvals based on an application rate of 220 microns DFT (Dry Film Thickness)

General

Improved worker safety - very low volatile organic solvent volume.

DAMAR QL FAST DRY

Health and Safety

- For detailed information refer to the Material Safety Data Sheet and label for this product.
- Provide adequate ventilation during use.
- When spraying wear a quality mask as inhalation of mist may cause respiratory irritation.
- Wear eye protection when handling as splashes to the eye may cause irritation.
- Product is NON FLAMMABLE.

NEW ZEALAND: Eastgate Business Park, 800 Te Ngae Road, Rotorua
PO BOX 7084, Te Ngae, Rotorua 3042, New Zealand
P: 0800 33 44 75 F: 0800 33 44 76 E: orders@damarindustries.co.nz
www.damarindustries.co.nz

AUSTRALIA: 25 Hargraves Place, Wetherill Park, NSW, 2164
PO BOX 6599, Wetherill Park 2164, Australia
P: +61 2 9756 4511 | F: +61 2 9756 0985
www.damarindustries.com.au

DISCLAIMER: This information is not a specification and is given in good faith. Since conditions of use are beyond the manufacturers control, all information given is without warranty, implied or otherwise, and is not intended to be exhaustive. Final determination for sustainability of the product for the use contemplated is the sole responsibility of the user. It is also the users responsibility to ensure that all information is current prior to using the product.