



Queens Road, Penkhull, Stoke-on-Trent, Staffordshire ST4 7LQ, United Kingdom

> tel: +44 (0)845 026 0902 fax: +44 (0)1782 412331 email: enquiries@ceram.com web: www.ceram.com

PHYSICAL TESTING REPORT

Far Eastern European Trading Company Ltd Unit 17 Rotherhithe Business Estate 214 Rotherhithe New Road London SE16 3EH

FAO: Mr Mike Hayward

REPORT OF TESTS ON: Porcela Bobo Porcel-Thin

Your Reference:

C1

CERAM Reference:

(12831)-3504

02-Mar-2012

Order Number:

N/A

Date Logged

Date Reported

14-Feb-2012

Date(s) of Test(s):

22-Feb-2012 to 22-Feb-2012

<u>Determination of Dimensions - Straightness of Sides</u>

BSENISO 10545-2: 1997

	AD	BA	CB	DC
No.	mm	mm	mm	mm
1	-0.45	-0.04	-0.21	0.01
2	-0.95	0.01	0.17	-0.01
3	0.10	-0.06	-1.86	0.00
4	0.14	-0.06	0.04	0.04
5	0.03	-0.02	0.11	-0.01
6	-0.38	-0.02	0.14	-0.02
7	-0.11	-0.01	0.12	0.01
8	-1.69	0.01	0.16	0.00
9	-0.67	0.00	-0.54	0.00
10	-0.54	0.02	0.03	-0.02

Description of Test Specimen(s): Floor tiles

Type of Tile (if known): B1a Work Size: 1200mm x 600mm

Maximum Deviation from Straightness: -0.31 % Permissible Deviation from Straightness: ± 0.50 %

Result for Straightness of Sides: Sample Complies with the requirements

Opinions and interpretations expressed herein are outside the scope of UKAS Accreditation.

End of Test Report

S Hall

Authorised Signatory



