



INSTRUCTIONS FOR CHANGING EQUIPMENT FROM SOLVENT TO WATERBASED USAGE

- 1. Flush all equipment with solvent thinner suitable for paint/lacquer product used
- 2. Flush again thoroughly with acetone
- 3. Change filters in pump and gun
- 4. Final thorough flush with clean water
- 5. Equipment ready to spray waterbased products

INSTRUCTIONS FOR CHANGING EQUIPMENT FROM WATER TO SOLVENT-BASED USAGE

- 1. Flush all equipment with clean water
- 2. Flush again thoroughly with acetone
- 3. Change filters in pump and gun
- 4. Final thorough flush with solvent thinner suitable for paint/lacquer product use
- 5. Equipment ready to spray solvent-based products

