



Owensboro Specialty Polymers, Inc.

Chemistry that Connects, People that Care

Owensboro Specialty Polymers, Inc.

5529 Highway 2830

Owensboro, KY 42303

www.onssp.com

DARATAK[®]

Adhesive Emulsions

Product Comparison Chart

Description	% Total Solids	Viscosity ¹ (cps)	pH	Particle Size (microns)	Clarity	Water Resistance	Tg°C
Borax Compatible Homopolymers							
61LT Medium viscosity, good water resistance, heat sealing, F/R mastics	55	2,000-4,000	4.5-5.5	1.0	Clear	Excellent	40
Non-Borax Compatible Homopolymers							
56L Very high molecular wt., low viscosity, fast drying, quick break	55	300-600	5.5-7.0	1.0	Slight haze	Good	37
17-200 Medium molecular wt., low-medium viscosity, general purpose, superior compounding & machining	55	1,500-2,000	4.5-6.0	1.5	Slight haze	Fair	31
Non-Borax Compatible Copolymers							
A Similar to "B" with greater hardness and less flexibility	55	1,000-1,400	4.0-5.5	1.5	Clear	Excellent	12
B Excellent compounding properties, bonds to non-porous substrates, good machining	55	1,000-1,400	4.0-5.5	1.5	Clear	Excellent	8
Special & Blended Systems							
90L Acrylic terpolymer; dries to permanently tacky film	55	2,000-4,000	4.5-5.5	1.0	Clear	Excellent	-18
SP1074 Acrylic terpolymer, dries to permanently tacky film, higher peel strength than 90L	55	1,000-1,700	4.0-5.5	1.0	Clear	Excellent	-25

¹ Brookfield LVF, 25°C

The information presented herein is based on the best available data and is believed to be true and accurate. Please read all statements, recommendations, or suggestions in conjunction with our conditions of sale which apply to all goods supplied by us. No responsibility for the use of these statements, recommendations, or suggestions is assumed by the supplier, nor are they intended as a recommendation for any use which would infringe any patent or copyright. The buyer bears sole responsibility for determining suitability of the product for their application.