



AXPOLY® PP51 1008

Product information sheet: Black copolymer polypropylene resin, with high melt flow

Description: Increased melt flow polymer for use in complex 3D moulded products with thinner wall thickness, where shot-time and surface finish are key performance factors.

Export tariff code: 3902100010

Product physical properties

Product grade: Axpoly® PP51 1008

Test parameter	Method	Unit	Value
Physical properties			
Density	ISO 1183	g/cm ³	0.96
Rheological properties			
Melt Flow (2.16 kg @ 230°C)	ISO 1133	g/10mins	10
Mechanical properties			
Tensile strength (@ 23°C)	ISO 527	MPa	20
Flexural Modulus (@ 23°C)	ISO 178	MPa	1300
Notched Izod Impact strength (@ 23°C)	ISO 180	kJ/m ²	12

Please note this polymer is not approved for use in food, medical or toy applications. All grades are tested to ISO standards, and certified as ROHS and REACH compliant.



The data is provided as a guide only and does not create any liability, warranty or guarantee of performance. The values may vary from the above information and do not indicate specific limits. This document does not create any liability, warranty or guarantee of product performance. It is the buyer's responsibility to determine the suitability of the material for the end application.

www.axiongroup.co.uk/AxpolyPolypropylene

Indigo Street, Off Langley Road South, Salford. M6 6RX
 Tel. +44 161 737 6124
 E. info@axionpolymers.com