

Method of Use

The adhesive is packed into 1.5 litre twin cartridges and packed 4 cartridges per box together with 6 mixer tubes, and is also available in 400ml twin cartridges packed 6 cartridges per box together with 8 mixer tubes.

1. Ensure the roof deck is dry do not apply if there is any standing water.
2. Remove the plastic cover from the top of the cartridge, then using a sharp knife cut the two caps off the top of the threaded head.
3. Screw on the plastic mixer tube ensuring it is tightly secured.
4. Place the cartridge in the applicator gun.
5. Dispense a small amount of adhesive until a consistent green colour is achieved.
6. Apply the adhesive in parallel beads 6 - 12mm in size.
7. Beads should be 300mm apart for normal roof exposure or 200mm apart for roof perimeters.
8. The insulation boards should be placed immediately into the wet adhesive.
9. The boards will be bonded within 10 minutes and work can continue.
10. If the mixed adhesive is left standing in the plastic mixer tube for more than 20 seconds it will thicken and a new mixer tube will be required.

Technical Data

Chemical base

Polyurethane

Viscosity

Part A : 7500 -12500cps at 20°C

Part B : 1500 - 2500cps at 20°C

Specific Gravity

Part A : 0.95 - 1.05

Part B : 1.15 - 1.25

Non -Volatile Content

100%

Solvents

None

Flammability

No Flash Point

Colour

Part A : Blue Part B : Yellow

Mixed : Green

Chemical Resistance

Resistant to water, dilute acids, alkalis

and aliphatic oils.

Coverage per 1500ml tube

Up to 14m² for normal roof exposure

Up to 9m² for roof perimeters