

Figure 4

PRO-BLK 10

Production-grade additive manufacturing material with game-changing thermoplastic-like mechanical properties and long-term environmental stability

Versatile rigid heat resistant material combines speed, strength, excellent mechanical properties for tool-less direct production of plastic parts

Figure 4 PRO-BLK 10 delivers on the promise of additive manufacturing with true direct digital production of plastic parts. Go from CAD to manufacturing line in one day with tool-less, same day part production. With a fast print speed and simplified post-processing that includes a single curing cycle and single solvent cleaning, this material delivers exceptional throughput. It is a high precision resin producing parts with a smooth surface finish and sidewall quality, and has excellent mechanical properties and long-term environmental stability that brings a new level of assurance to 3D production.



Applications

- ▶ Tool-less, same day production
- ▶ Direct production of small black plastic parts; examples include: motor housings, connectors, snap-fits, automotive interior and other general-use parts
- ▶ Digital production to replace injection moulding or soft tooling processes

Benefits

- ▶ Improved environmental stability of mechanical and performance properties over time
- ▶ Fast throughput for part-in-hand with no secondary thermal cure required
- ▶ Simple, single solvent cleaning
- ▶ Excellent surface quality and repeatability
- ▶ Accurate, low distortion material for fast first article print success

Features

- ▶ Fast print speed up to 62 mm/hr at 50 micron layer thickness
- ▶ 70 °C heat deflection temperature, 12% elongation at break
- ▶ Durability and strength

Liquid Material

LIQUID PROPERTIES			
MEASUREMENT	CONDITION	METRIC	U.S.
Viscosity	@ 25 °C (77 °F)	293 cps	709 lb/ft-hr
Colour		Black	
Liquid Density	@ 25 °C (77 °F)	1.07 g/cm ³	0.039 lb/in ³
Layer Thickness (Standard Mode)		0.05 mm	0.002 in

Figure 4

PRO-BLK 10

Production-grade additive manufacturing material with game-changing thermoplastic-like mechanical properties and long-term environmental stability

Post-Cured Material

MECHANICAL PROPERTIES			
MEASUREMENT	CONDITION	METRIC	U.S.
Solid Density (g/cm ³ lb/in ³)	ASTM D792	1.16	0.042
Tensile Strength, Ultimate (MPa PSI)	ASTM D412	63	9140
Tensile Strength, at Yield (MPa PSI)	ASTM D412	63	9140
Tensile Modulus (MPa KSI)	ASTM D412	2320	336
Elongation at Break	ASTM D412	12%	
Elongation at Yield	ASTM D412	4.7%	
Flexural Strength (MPa PSI)	ASTM D790	92	13340
Tensile Modulus (MPa KSI)	ASTM D790	2290	332
Notched Izod Impact Strength (J/m Ft-lbs/in)	ASTM D256	24	0.5
Unnotched Izod Impact Strength (J/m Ft-lbs/in)	ASTM D4812	136148	11.5
Glass Transition (T _g), DMA, E''	ASTM E1640	62 °C	144 °F
Heat Deflection Temperature @ 0.45 MPa (66 PSI)	ASTM D648	70 °C	158 °F
@ 1.82 MPa (264 PSI)		56 °C	133 °F
Coefficient of Thermal Expansion (CTE) (ppm/°C ppm/°F)	ASTM E831	< T _g	39
		> T _g	104
Hardness, Shore	ASTM D2240	79D	
Water Absorption (24 hour)	ASTM D570	1.16%	



Warranty/Disclaimer: The performance characteristics of these products may vary according to product application, operating conditions, material combined with, or with end use. Prototype Projects makes no warranties of any type, express or implied, including, but not limited to, the warranties of merchantability or fitness for a particular use.

© 2019 by Prototype Projects Ltd. All rights reserved. Images courtesy of 3D Systems. Figure 4 is a trademark of 3D Systems, Inc.