

TECHNICAL DATA SHEET

Shuman Compound:

Polystyrene Medium Impact 811 Utility Black, 881 Grey

Offers this combination of properties:

Easy processability, Good gloss, Good surface appearance

TYPICAL PROPERTIES

MECHANICAL PROPERTIES Izod Impact Strength (Notched, 1/8" Thick Specimen) Rockwell Hardness Tensile Strength	VALUE 0.9-1.3 60 5200	<u>UNITS</u> FT-LBS/IN L PSI	TEST METHODS ASTM D-256 ASTM D-785 ASTM D-638
THERMAL PROPERTIES Heat Deflection Temperature @ 264 PSI Vicat Softening Temperature	190 210	deg. F deg. F	ASTM D-648 ASTM D-1525
OTHER PROPERTIES Specific Gravity	1.05		ASTM D-792

SUGGESTED PROCESSING CONDITIONS

6 (+/-2)

8 (+/-2) 10 (+/-2) GM/10 MIN.

ASTM D-1238

TEMPERATURE CONDITIONS:

400 - 440F

Melt Flow Rate

NOTICE: THE INFORMATION CONTAINED HEREIN IS BASED ON WHAT WE BELIEVE TO BE RELIABLE DATA, BUT SHUMAN PLASTICS, INC. MAKES NO WARRANTIES EXPRESS OR IMPLIED, INCLUDING, BUT NOT LIMITED TO, THE IMPLIED WARRANTIES OR MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE. BECAUSE SHUMAN HAS NO CONTROL OVER THE USE TO WHICH OTHERS MAY PUT THE PRODUCT, IT DOES NOT SUGGEST OR REPRESSENT THAT THE SAME RESULTS AS THOSE REFERRED TO HEREIN WILL BE OBTAINED BY ANOTHER USER. EACH USER OF THE PRODUCT AND THE COMPOSITIONS MENTIONED HEREIN SHOULD MAKE HIS OWN TESTS PRIOR TO PURCHASE TO DETERMINE THE PRODUCT'S SUITABILITY FOR HIS OWN PARTICULAR USES.

NOTHING CONTAINED HEREIN IS TO BE CONSTRUED AS A RECOMMENDATION FOR THE USE IN VIOLATION OF ANY EXISTING PATENT, FOREIGN OR DOMESTIC, OR OF APPLICABLE LAWS AND REGULATIONS.

DATA SHOWN ARE THE AVERAGE RESULTS OF OUR OWN TESTS AND SHOULD NOT BE USED FOR SPECIFICATIONS

DOC REV 11/17