

HIGHLIGHTS

LOW-LEVEL 1

Style
Tufted loop pile 1/10

Yarn Construction
100% PA 6 Aqualon™

Pile Yarn Weight
530 gsm

Pile Height
6mm

Pile Density
160,000 tufts per m²

Total Weight
4650 gsm

Total Thickness
6mm

Backing
Bitumen

Dimensions
50cm x 50cm

Wear Classification
Heavy Contract 33-LC1

Anti-static
Suitable for use with computers.
Less than 2Kv

Colour Fastness
To Light (BS EN ISO105-B02) 5 - 6
To Water (BS EN ISO105-E01) 4
To Rubbing (BS EN ISO105-X12) 4
Flammability BFL-S1 EN 13501-1

Castor Chair Test
BS EN 985 2.4 Suitable for use with castor chairs
continuous use

Warranty
10 Years

VOC Content E1 in relation to EN 14041:2004

MULTI-LEVEL 3

Style
Tufted 1/12th Loop

Yarn Construction
100% PA6 Aqualon

Pile Yarn Weight
670 gsm

Pile Height
4.1mm

Pile Density
240,000 g/cm³

Total Weight
4800 gsm

Total Thickness
7.7mm

Backing
Bitumen

Dimensions
50cm x 50cm

Wear Classification
Heavy Contract

Anti-static
Suitable for use with computers.
Less than 2Kv

Colour Fastness
To Light (BS EN ISO105-B02) 5
To Water (BS EN ISO105-E01) 4
To Rubbing (BS EN ISO105-X12) 4

Flammability
BFL-S1 EN 13501-1

Castor Chair Test
BS EN 985 2.4 Suitable for use with castor chairs
continuous use

Warranty
10 Years

VOC Content E1 in relation to EN 14041:2004

STRUCTURED 2

Style
Tufted loop pile 1/10

Yarn Construction
100% Polyamide

Pile Yarn Weight
850 gsm

Pile Height
3.5mm

Pile Density
104,000 tufts per m²

Total Weight
600 gsm

Total Thickness
7mm

Backing
Bitumen

Dimensions
50cm x 50cm

Wear Classification
Heavy Contract

Anti-static
Suitable for use with computers.
Less than 2Kv

Colour Fastness
To Light (BS EN ISO105-B02) 5
To Water (BS EN ISO105-E01) 4
To Rubbing (BS EN ISO105-X12) 4

Flammability
BFL-S1 EN 13501-1

Castor Chair Test
BS EN 985 2.4 Suitable for use with castor chairs
continuous use

Warranty
10 Years

VOC Content E1 in relation to EN 14041:2004

STROBE 5

Style
1/10th gauge

Yarn Construction
Solution Dyed / Space Dyed

Pile Yarn Weight
610 gsm (8226 580gsm)

Pile Height
3mm

Total Weight
4390 gsm

Total Thickness
6mm

Backing
Bitumen

Dimensions
50cm x 50cm

Wear Classification
Heavy Contract

Anti-static
< 2kV body voltage
Suitable for use with computers

Colour Fastness
To Light (ISO105 - B02) > 6
To Water (ISO 105 - E01) > 5
To Rubbing (ISO 105 - X12) > 5 dry 4-5 wet

Flammability
Flammability (BS5267) Assessment and labeling
of Textile Floor coverings tested to BS4790
Low radius of Char
(Hot Metal Nut Test) CE Flam rating - Bfl-s1

Castor Chair Test
BS EN 985 continuous use

Warranty
10 Years

VOC Content E1 in relation to EN 14041:2004

CUTPILE

Style
Tufted 1/10 Frisé Cutpile

Yarn Construction
100% PA 6.6 Antron™

Pile Yarn Weight
1050 gsm

Pile Height
5mm

Pile Density
181,102 tufts per m²

Total Weight
4650 gsm

Total Thickness
8mm

Backing
Bitumen

Dimensions
50cm x 50cm

Wear Classification
Heavy Contract

Anti-static
Suitable for use with computers.
Less than 2Kv

Colour Fastness
To Light (BS EN ISO105-B02) 5
To Water (BS EN ISO105-E01) 4
To Rubbing (BS EN ISO105-X12) 4

Flammability
BFL-S1 EN 13501-1

Castor Chair Test
BS EN 985 2.4 Suitable for use with castor chairs
continuous use

Warranty
10 Years

VOC Content E1 in relation to EN 14041:2004



BREEAM® 'A+' Rated